



CERTIFICATIONS AUTHORITIES



CSI
Certificazione e Testing

EXOVA



Description: Bituminous viscoelastic damping materials. Mixed with elastomeric filler and mineral charges, which are all combined to obtain a high density with a relatively low thickness. Available with self adhesive.

Application: Anti damping, anti vibration material.

Finishing: Laminated with aluminum foil in various thickness, smooth or diamond pattern.

Weight: From 2,5 to 12 Kg/Sqm

Thickness: From 1,5 to 6mm

Temperature resistance: +100 °C – 2 hours

Working temperature: From -30°C to +90°C

Fire resistance: Selfextinguible, flame propagations speed £ 100 mm/min - ISO 3795.

Stocking time: 3 months max.

Working instruction: Our bitumen sheet should be stored at a room temperature of around 10°C min. or allowed to stabilise prior to use at room temperature for several hours. The self-adhesive will satisfactorily bond at 18°C. However the adhesion can be enhanced if the material is pre-heated to 30°C.

Don not attempt to handle this material at below -5°C as the material become brittle and breakable.